

## CU-PRO UNDERWATER PRIMER

---

### Product description

CU-PRO Underwater Primer is a modified chlorinated rubber primer for use with CU-PRO Premium Antifouling.

---

### Recommended use

For use on boat hulls as a primer or tie coat over unknown or hard antifouling.

---

### Substrates

GRP, wood, steel and ferro cement and aluminium.

---

### Packing (typical)

2.5 Litres

---

### Product Data

Colours:	Silver/Grey
Finish:	Matt
Volume solids:	37%
Theoretical spreading rate:	10 sq.metres per litre
Flash point:	25°C
Specific gravity:	1.70
Dry to touch:	30 min (@ 23 °C)
Over-coating timw:	8 hours (@ 23 °C)

**DATA SHEET**  
**CU-PRO UNDERWATER PRIMER**

---

\*The theoretical spreading rate has been calculated for the stated volume solids and dry film thickness. A practical spreading rate will depend on the actual dry film thickness, the nature of the substrate, and the relevant consumption factor. The physical constants are subject to normal manufacturing tolerances.

---

**Application Details**

Application method: Brush, solvent resistant roller or spray (airless, pressure pot or HVLP only).

Thinner: Cu-Pro Thinners

Cleaning of tools: Cu-Pro Thinners

Surface condition: The surface should be stable, firm, dry and free of dust, sand, loose old paint, dirt, grease, oil and salt.

Please refer to the Material Safety Data Sheet for further information.

For additional guidance please contact your local Technical Sales Representative.

If using multiple cans please check batch numbers are the same

---